

Innovium REPAIR : Oil & Gas applications

Product	Process	Viscosity	Gel time (min) on 100g @ 25°C	pH resistance	Tg °C (°F)	Purpose	Comments
XIN 4060	Lay-up	Putty	30-45	From 3 to 12	60 (140)	Corrosion repair and pipe strengthening	High chemical resistance. Suitable for oil, gas, water
XIN 4080	Lay-up	Putty	60	From 3 to 12	80 (176)		
XIN 4160	Casting	Viscous liquid	30-45	From 3 to 12	60 (140)		
XIN 4180	Casting	Viscous liquid	60	From 3 to 12	80 (176)		
XIN Subsea	Lay-up	Putty	105	From 3 to 12	50 (122)	Under water solution for corrosion repair and pipe strengthening	
XIN Subsea prim	Lay-up	Viscous liquid	15	From 3 to 12	70 (158)	Under water primer for under water pipe preparation and preventive treatment	High chemical resistance, High adhesion on substrate, High reactivity