

**Innovium REPAIR : Oil & Gas applications**

Product	Process	Viscosity	Gel time (min) on 100g @ 25°C	pH resistance	Tg °F [°C]	Purpose	Comments
AKD 4060	Layup	Putty	30-45	From 3 to 12	140 (60)	Corrosion repair and pipe strengthening	High chemical resistance. Suitable for oil, gas, water
AKD 4080	Layup	Putty	60	From 3 to 12	176 (80)		
AKD 4160	Casting	Viscous liquid	30-45	From 3 to 12	140 (60)		
AKD 4180	Casting	Viscous liquid	60	From 3 to 12	176 (80)		
AKD Subsea	Layup	Putty	105	From 3 to 12	122 (50)	Under water solution for corrosion repair and pipe strengthening	
AKD Subsea prim	Layup	Viscous liquid	15	From 3 to 12	158 (70)	Under water primer for under water pipe preparation and preventive treatment	High chemical resistance. High adhesion on substrate. High reactivity