



Innovium High Tg solutions

Semi-solid epoxy resin films

Product	Process	Viscosity @ 60°C (mPa.s)	GC* (J/m²)	Recommended cure	Tg °C (°F)	Storage modulus* GPa (kPSI)	Film density (g/sqm)	Film thickness (µm)	Comments
LEO 2376	Preimpregnation, RFI	160 000	430	2h @ 130°C (266°F) + 2h @ 200°C (392°F)	160 (320)	50 (7250)	40 - 400	35 - 350	Semi solid resin films are designed for a simple implementation in common production lines to produce prepreg. On-the-shelf formulations are low tack versions. Tack may be adjusted on-demand.
LEO 2377	Preimpregnation, RFI	260 000	630		160 (320)	47 (6800)	40 - 400	35 - 350	
LEO 2378	Preimpregnation, RFI	350 000	880		160 (320)	44 (6400)	40 - 400	35 - 350	

* Values determined on carbon based fibre composite (8 layers) cured in autoclave

Innovium Low Tg solutions

Semi-solid epoxy resin film

Product	Process	Viscosity @ 60°C (mPa.s)	Impact resistance	Recommended cure	Tg °C (°F)	Flexural modulus MPa (PSI)	Flexural strength MPa (PSI)	Film density (g/sqm)	Film thickness (µm)	Comments
LEO 5529	Preimpregnation, RFI	Coming soon	Coming soon	1h @ 130°C (266°F)	120 (248°F)	Coming soon	Coming soon	40 - 400	35 - 350	Semi solid resin films are designed for a simple implementation in common production lines to produce prepreg. On-the-shelf formulations are low tack versions. Tack may be adjusted on-demand. Storage conditions: 6 months at room temperature.
LEO 1607	Preimpregnation, RFI	Coming soon	Coming soon		120 (248°F)	Coming soon	Coming soon	40 - 400	35 - 350	
LEO 1608	Preimpregnation, RFI	370 000	Coming soon		120 (248°F)	Coming soon	Coming soon	40 - 400	35 - 350	